

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 1 047 121 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

25.10.2000 Bulletin 2000/43

(51) Int. Cl.<sup>7</sup>: **H01L 21/306**, H05K 3/26,

C11D 7/26, B08B 3/08,

C11D 1/02, C11D 1/66

(21) Application number: 00108565.3

(22) Date of filing: 19.04.2000

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE

Designated Extension States:

AL LT LV MK RO SI

(72) Inventors:

- Ishikawa, Norio  
Soka-shi, Saitama-ken (JP)
- Abe, Yumiko  
Soka-shi, Saitama-ken (JP)
- Mori, Kiyoto  
Soka-shi, Saitama-ken (JP)

(30) Priority: 20.04.1999 JP 11156999

(71) Applicant:

Kanto Kagaku Kabushiki Kaisha  
Tokyo (JP)

(74) Representative:

Vossius, Volker, Dr. et al  
Dr. Volker Vossius,  
Patentanwaltskanzlei - Rechtsanwaltskanzlei,  
Holbeinstrasse 5  
81679 München (DE)

(54) **Cleaning solution for substrates of electronic devices**

(57) The present invention relates to a cleaning solution capable of removing efficiently at the same time particles and metallic impurities from a substrate surface without corroding metallic materials.

The cleaning solution for cleaning substrates of electronic materials comprises an organic acid compound and at least one selected from the group consisting of dispersants and surfactants.

EP 1 047 121 A1

## Description

## BACKGROUND OF THE INVENTION

5 [0001] The invention relates to a cleaning solution for substrates of electronic materials, and particularly to a cleaning solution for removing metallic impurities and particle contamination adsorbed by substrates having metallic wiring in semiconductor manufacturing.

[0002] A trend for higher integration of ICs has brought about the need for strict contamination control, because trace impurities have a considerable effect on the properties and yield of devices. Which means that the concentration of metallic impurities and the presence of particles on the substrate need to be strictly controlled; for this purpose different types of cleaning solutions are used in the different processes of semiconductor manufacturing.

10 [0003] In general, mixed solutions of sulfuric acid-aqueous hydrogen peroxide, ammonium water-aqueous hydrogen peroxide-water (SC-1), hydrochloric acid-aqueous hydrogen peroxide-water (SC-2), diluted hydrofluoric acid, etc. are used as cleaning solutions for cleaning substrates of electronic materials such as semiconductor substrates, and depending on the purpose, each cleaning solution can be used on its own or in combination with other cleaning solutions.

[0004] Further, in recent years chemical mechanical polishing (CMP) technology has been introduced into semiconductor manufacturing processes for the planarization of insulation films, the planarization of contact holes, for damascene wiring, etc. CMP is a technology for polishing and planarizing insulation films and metallic materials by simultaneously using the chemical and physical effects, when a wafer is pressed against a polishing cloth called buff and is rotated while feeding a slurry, a mixture of abrasive particles and chemicals.

20 [0005] The slurry used in metal CMP (W and Cu-CMP) is a combination of abrasive particles (alumina, silica, manganese dioxide, cerium oxide, zirconium oxide, etc.) and an oxidizer (Iron(III) nitrate, aqueous hydrogen peroxide, etc.). Therefore, after the CMP process, the substrate surface is contaminated by metallic impurities and abrasive particles from the slurry, as well as by polishing waste. Especially when Iron(III) nitrate is used as oxidizer, there is the fear that due to the contamination by a high Fe concentration, a secondary contamination, polluting the production line, occurs in addition to the deterioration of the electrical properties of the substrate itself.

[0006] Consequently, the metallic impurities and the particles adhering during the CMP process need to be speedily removed before passing to the next process.

30 [0007] In the CMP treatment of interlayer insulation films, dilute hydrofluoric acid is used for removing metallic impurities and ammonia water is used for removing particles.

[0008] However, since dilute hydrofluoric acid corrodes metallic materials it cannot be used for cleaning after Cu and W-CMP.

35 [0009] An aqueous solution of citric acid is reported in Semiconductor World, p. 92, No. 3, 1997 as a cleaning solution not corroding metallic materials. Moreover, JP, A, H10-72594 proposes a method for improving the capacity for removing metallic impurities by combining citric acid and other organic acids with a complexing solution. However, these cleaning solutions of organic acids are insufficient for removing metallic impurities and incapable of removing particles.

40 [0010] Ammonia water used for removing particles also corrodes copper, hence it is not suitable as cleaning solution after Cu-CMP. Moreover, the use of 2 types of cleaning solution for the cleaning process complicates the production processes and considerably increases the amount of chemicals used. Consequently, a new cleaning technology capable of removing particles and metallic impurities without corroding metallic materials is also needed from the cost point of view and for the protection of the environment.

[0011] Thus, when cleaning substrates of electronic materials, a cleaning solution for performing a simple and efficient cleaning without going through a troublesome process is strongly required.

45 [0012] I.e., the object of the present invention is to provide a cleaning solution for substrates of electronic materials capable of removing at the same time metallic impurities and particles from the substrate surface without corroding metallic materials.

50 [0013] In the present invention, the term substrate for electronic materials embraces semiconductor wafers, color filters, substrates of electronic devices for thin-film applications (flat panel devices such as liquid crystals, plasma, EL, etc., optic and magnetic discs, CCD, etc.), etc.

## SUMMARY OF THE INVENTION

55 [0014] As a result of extensive research to achieve the above-mentioned object, the inventors of the present invention have completed the invention by finding that, surprisingly, adsorbed metallic impurities and particles can both be cleaned very efficiently at the same time without the corrosion of metal by adding dispersants and/or surfactants to an aqueous solution of organic acids such as oxalic acid, etc.

[0015] I.e., the present invention relates to a cleaning solution for cleaning substrates of electronic materials comprising one or more organic acid compounds and at least one selected from the group consisting of dispersants and surfactants.

[0016] The invention further relates to the before-mentioned cleaning solution, wherein the organic acid compound is one or more member(s) selected from the group consisting of oxalic acid, malonic acid, succinic acid, malic acid, tartaric acid, citric acid and their ammonium salts.

[0017] The invention further relates to the before-mentioned cleaning solution, wherein the surfactant is an anionic or a nonionic surfactant.

[0018] The invention further relates to the before-mentioned cleaning solution, wherein the dispersant is one or more member(s) selected from a group consisting of condensed phosphoric acids and phosphates.

[0019] The invention further relates to the before-mentioned cleaning solution, wherein the organic acid compound is 0.01 to 30 mass percentages.

[0020] The invention further relates to the before-mentioned cleaning solution, wherein the dispersant and the surfactant are 0.0001 to 10 mass percentages.

[0021] The invention further relates to the before-mentioned cleaning solution, wherein a chelating agent is further comprised.

[0022] The invention further relates to the before-mentioned cleaning solution, wherein a water-soluble alcohol is further comprised.

[0023] The invention further relates to the before-mentioned cleaning solution, wherein the metallic impurities and the particle contamination adsorbed by a substrate are both removed at the same time.

[0024] The invention further relates to the before-mentioned cleaning solution, wherein the substrate of electronic materials is a substrate to which metallic wiring has been applied.

[0025] The invention further relates to the before-mentioned cleaning solution used after chemical mechanical polishing.

[0026] The cleaning mechanism of the cleaning solution according to the present invention is not necessarily clear; however, the following reason can be presumed. Ordinarily, the particles in an aqueous solution have an electric charge called zeta potential, which also applies to semiconductor substrates. If the electric charge of the substrate and the particles are of the opposite sign, the particles are adsorbed by the substrate due to the attractive force between substrate and particles. But if they are of the same sign, the particles are not adsorbed by the substrate due to the repulsive force. I.e., it is thought that by controlling the zeta potential, the adsorption of particles can be prevented and adsorbed particles can be removed. One of the important factors for controlling the zeta potential is the pH value. On the alkaline side at a pH of 8 or more, when most substances have a negative electric charge, the adsorption of particles is suppressed and their desorption is made easy. It is thought that for such reasons alkalies such as ammonia are traditionally used for removing particles.

[0027] It is further thought that zeta potentials can also be controlled by adding surfactants and a dispersant. The method using a dispersant and surfactants according to the present invention does not change liquidity very much and is therefore preferable as a method for solving the problem.

#### PREFERRED EMBODIMENTS OF THE INVENTION

[0028] The organic acid compound used in the present invention is selected from aliphatic monocarboxylic acids such as formic acid, acetic acid, propionic acid, etc.; dicarboxylic acids such as oxalic acid, malonic acid, succinic acid, etc.; hydroxylated polycarboxylic acids such as tartaric acid, malic acid, citric acid, etc.; and their ammonium salts. Among these, polycarboxylic acids are preferably used as organic acid compounds in the present invention because they are highly effective for removing metallic impurities.

[0029] The concentration of the organic acid compound in the cleaning solution is 0.01 to 30 mass percentages, and particularly preferable is 0.03 to 10 mass percentages. If the concentration of the organic acid compound is too low, the cleaning performance is insufficient; if however an overly high concentration is used, it is impossible to achieve an effect matching the concentration. Moreover, the concentration is also determined in consideration of the solubility of the organic acid and so as to avoid crystallization.

[0030] Moreover, any dispersant and surfactant may be used as long as the desired object of the present invention can be achieved. As dispersant condensed phosphoric acids such as metaphosphoric acid, pyrophosphoric acid, etc., and phosphates such as phytic acid, di(polyoxyethylene)alkylether phosphoric acid, tri(polyoxyethylene)alkylether phosphoric acid, etc. are typically used; e.g., di(polyoxyethylene)alkylether phosphoric acid is commercially available under the trade names of NIKKOL DDP-8, NIKKOL DDP-10, etc. and tri(polyoxyethylene)alkylether phosphoric acid is commercially available under the trade names of NIKKOL TDP-8, NIKKOL TDP-10, (all of Nikko Chemicals Co., Ltd.) etc. Further, as surfactant anionic or nonionic surfactants are typically used; anionic surfactants with a sulfonic group or a carboxyl group which are highly hydrophilic and nonionic surfactants whose hydrophilic properties can be increased

by the length of the ethylene oxide chain are particularly effective; specifically, polyethylene nonylphenylether and sorbitan type nonionic surfactants, e.g. commercially available under the trade names of Emulgen MS-110, Rheodol Super TW-0120 (of KAO Soap Co., Ltd.), sulfonic acid or sulfonate type anionic surfactants, e.g. commercially available under the trade names of Newcol 210, Newcol 560SF, Newcol 707SF (of Nippon Nyukazai Co., Ltd.) and further anionic high molecular surfactants can be mentioned. As anionic high molecular surfactants, e.g., 1) naphthalenesulfonic acid and formaldehyde condensates and their salts, 2) polymers with carboxylic acids such as acrylic acid, methacrylic acid, etc. and their salts and 3) lignosulfonic acid and its salts can be given as examples. 1) is commercially available under the trade names of Demol N, Demol AS (of KAO Soap Co., Ltd.), Polystar NP-100 (of Nihon Yushi Company), Runox 1000, 1000C, 1500A (of Toho Chemical Industry Co., Ltd.), Ionet D-2, Sanyo Levelon PHL (of Sanyo Chemical Industries, Ltd.), Loma PWA-40 (of Sannopku Co., Ltd.), etc.; Demol AS and Loma PWA-40 which are ammonium salts or free acids not containing metallic impurities are particularly preferable. 2) is commercially available under the trade names of Demol EP, POIZ 520, POIZ 521, POIZ 532A (of KAO Soap Co., Ltd.), Polystar A-1060, Polystar OM, Polystar OMA (of Nihon Yushi Company), Polity 530, Polity 540, Polity 550 (of Lion Corporation), Carrybon B, Carrybon L-400, Elem-Inol MBN-1, Sanspal PS-2, Sanspal PS-8, Sanspal PDN-173, Sanspal PS-30, Toxanon GR-31A, Toxanon GR-30, Toxanon NSA-400 (of Sanyo Chemical Industries Ltd.), Disrol H14N (of Nippon Nyukazai Co., Ltd.), etc.; POIZ 532A and Polystar OMA which are ammonium salts or free acids are particularly preferable. 3) is commercially available under the trade name of Sorpol 9047K (of Toho Chemical Industry Co., Ltd.).

[0031] The concentration of the dispersant and the surfactant is 0.0001 to 10 mass percentages, preferable 0.001 to 1.0 mass percentages, and most preferably 0.001 to 0.1 mass percentages. If the concentration of the dispersant is low, the removing performance is insufficient; if however it is too high, it is impossible to achieve an effect matching the concentration.

[0032] Moreover, water-soluble alcohols can be added to increase the affinity of the cleaning solution according to the present invention with the substrate and to suppress the foaming of the surfactant.

[0033] As water-soluble alcohols methanol, ethanol, 1-propanol, 2-propanol, 2-methyl-1-propanol, 2-methoxyethanol, etc. can be used. The concentration of the water-soluble alcohols is 0.01 to 30 mass percentages, particularly preferable is 1 to 10 mass percentages.

[0034] A chelating agent can also be added to further improve the ability for removing metallic impurities of the cleaning solution according to the present invention.

[0035] As chelating agent polyaminocarboxylic acids and their ammonium salts are preferred, specifically ethylene diamine tetraacetic acid, nitrilotriacetic acid, trans-1,2-cyclohexanediamine tetraacetic acid and their ammonium salts can be mentioned. The concentration of the chelating agent is 0.0001 to 0.1 mass percentages, particularly preferable is 0.0001 to 0.01 mass percentages.

## EXAMPLES

[0036] The Examples and Comparative Examples given below are to explain the present invention in detail and not to limit it.

[0037] The cleaning solutions according to the present invention and the cleaning solution used for comparison were prepared according to Table 1.

Table 1

Cleaning solution	Organic acid compound (mass percentages)	Dispersant, surfactant, chelating agent, water soluble alcohol (mass percentages)	
Example 1	Oxalic acid 0.34	Disrol H14N	0.01
Example 2	Oxalic acid 0.34	Polity 550	0.01
Example 3	Oxalic acid 0.34	Sorpol 9047K	0.01
Example 4	Oxalic acid 0.34	Newcol 707SF	0.01
Example 5	Oxalic acid 0.34	Rheodol Super TW-0120	0.01
Example 6	Oxalic acid 0.34	Pyrophosphoric acid	0.01
Example 7	Oxalic acid 0.34	Demol AS	0.01
Example 8	Oxalic acid 0.03	Demol AS	0.001
Example 9	Oxalic acid 3.40	Demol AS	0.1

Table 1 (continued)

Cleaning solution	Organic acid compound (mass percentages)	Dispersant, surfactant, chelating agent, water soluble alcohol (mass percentages)	
Example 10	Oxalic acid 0.34	Phytic acid	0.01
Example 11	Oxalic acid 0.34	NIKKOL TDP-8	0.01
Example 12	Oxalic acid 0.34	Newcol 560SF	0.01
		Phytic acid	0.01
		2-propanol	1.0
Example 13	Malonic acid 0.5	Demol AS	0.1
Example 14	Citric acid 10.0	Demol AS	1.0
Example 15	Ammonium oxalate 0.2	Newcol 707SF	0.01
Example 16	Oxalic acid 0.34	Ethylene diamine tetraacetic acid diammonium salt	0.01
		Newcol 560SF	1.0
Example 17	Triammonium citrate 1.0	Phytic acid	1.0
		Nitrilotriacetic acid	0.01
Example 18	Oxalic acid 2.0	Newcol 560SF	0.01
		Phytic acid	0.01
		2-propanol	10.0
Comp.Ex. 1	Oxalic acid 0.34	---	
Comp.Ex. 2	Citric acid 0.50	---	
Comp.Ex. 3	---	Demol AS	0.01
Comp.Ex. 4	Oxalic acid 0.34	tetradecyl trimethyl-ammonium chloride	0.01
Note: • Disrol H14N, Newcol 560SF and Newcol 707SF are products of Nippon Nyukazai Co., Ltd. • Polity 550 is a product of Lion Corp. • Sorpol 9047K is a product of Toho Chemical Industry Co., Ltd. • Rheodol Super TW-0120 and Demol AS are products of KAO Soap Co., Ltd. • NIKKOL TDP-8 is a product of Nikko Chemicals Co., Ltd.			

[0038] The following Experiments were conducted with the prepared cleaning solution.

(0019)

#### Experiment 1 (Particle removing performance 1: alumina particles)

[0039] Soaked in a CMP slurry (WA-355: Fe-20 = 1:1 mixed solution, oxidizer: Iron(III) nitrate, abrasive particles: alumina) manufactured by Cabot Corp., 4-inch  $\phi$  silicon wafers (about 10000 particles of 0.24  $\mu\text{m}$  or more) with an oxide film were contaminated beforehand by particles, cleaned for 3 min. at 25 °C with the cleaning solutions of Examples 1 to 18 and Comparative Examples 1 to 4, rinsed and dried, after which the number of particles was measured with a wafer surface inspection device Surfscan 4500 (manufactured by KLA-Tencor Corp.). The number of particles before and after the cleaning process was compared, and the capacity for removing particles of the respective cleaning solutions was evaluated. The result is shown in Table 2.

Table 2

Cleaning solution	Particle (alumina) removing ratio (%)
Example 1	98.8
Example 2	97.1
Example 3	95.0
Example 4	94.6
Example 5	97.8
Example 6	99.2
Example 7	90.1
Example 8	93.7
Example 9	99.6
Example 10	98.7
Example 11	94.3
Example 12	99.1
Example 13	95.6
Example 14	98.5
Example 15	92.2
Example 16	97.8
Example 17	98.2
Example 18	99.3
Comp. Example 1	42.0
Comp. Example 2	60.4
Comp. Example 3	46.7
Comp. Example 4	12.7

#### Experiment 2 (Particle removing performance 2: silica)

[0040] Soaked in an aqueous solution in which silica particles (with a diameter of 0.3 $\mu$ m) were dispersed, 4-inch  $\phi$  silicon wafers (about 13000 particles of 0.24  $\mu$ m or more) with an oxide film were contaminated beforehand by particles, cleaned for 3 min. at 25 °C with the cleaning solutions of Examples 4, 5, 12-16, 18 and Comparative Example 1, rinsed and dried, after which the number of particles was measured with a wafer surface inspection device Surfscan 4500 (manufactured by KLA-Tencor Corp.). The number of particles before and after the cleaning process was compared, and the capacity for removing particles of the respective cleaning solutions was evaluated. The result is shown in Table 3.

Table 3

Cleaning solution	Particle (silica) removing ratio (%)
Example 4	91.9
Example 5	89.5
Example 12	98.1

Table 3 (continued)

Cleaning solution	Particle (silica) removing ratio (%)
Example 13	97.5
Example 14	98.3
Example 15	95.3
Example 16	97.9
Example 18	96.2
Comp. Example 1	54.2

### Experiment 3 (Fe removing performance)

[0041] 4-inch  $\phi$  silicon wafers with an oxide film were contaminated beforehand with Fe by soaking them in a 0.1 mass percentage aqueous solution of Iron(III) nitrate, after which the Fe concentration at the wafer surface was measured by using a total reflection fluorescence X-ray device (TREX-610T manufactured by Technos Co., Ltd.).

[0042] The wafers were cleaned for 3 min. at 25°C with the cleaning solutions of Examples 1 to 6 and Comparative Examples 1 and 2, rinsed and dried, after which the Fe concentration at the wafer surface was again measured, and the capacity for removing Fe was evaluated. The result is shown in Table 4.

Table 4

Cleaning solution	Fe concentration ( $\times 10^{10}$ atoms/cm <sup>2</sup> )
Before cleaning	about 7600
Example 1	2.6
Example 2	3.0
Example 3	2.4
Example 4	2.8
Example 5	3.8
Example 6	2.7
Comp. Example 1	4.7
Comp. Example 2	321

[0043] It is clear from the above that the cleaning solutions according to the present invention show excellent performances for removing particles and metallic impurities.

### Claims

1. A cleaning solution for cleaning substrates of electronic materials comprising one or more organic acid compounds and at least one selected from the group consisting of dispersants and surfactants.
2. The cleaning solution according to claim 1, wherein the organic acid compound is one or more member(s) selected from the group consisting of oxalic acid, malonic acid, succinic acid, malic acid, tartaric acid, citric acid and ammonium salts thereof.
3. The cleaning solution according to claim 1, wherein the surfactants is an anionic or a nonionic surfactant.
4. The cleaning solution according to claim 1, wherein the dispersant is one or more member(s) selected from the group consisting of condensed phosphoric acids and phosphates.

**EP 1 047 121 A1**

5. The cleaning solution according to claim 1, wherein the organic acid compound is 0.01 to 30 mass percentages.
6. The cleaning solution according to claim 1, wherein the dispersants and the surfactants are 0.0001 to 10 mass percentages.
- 5 7. The cleaning solution according to claim 1, wherein a chelating agent is further comprised.
8. The cleaning solution according to claim 1, wherein a water-soluble alcohol is further comprised.
- 10 9. The cleaning solution according to any one of claims 1 to 8, wherein the metallic impurities and the particle contamination adsorbed by a substrate are both removed at the same time.
10. The cleaning solution according to any one of claims 1 to 9, wherein the substrate of electronic materials is a substrate to which metallic wiring has been applied.
- 15 11. The cleaning solution according to claim 10, used after chemical mechanical polishing.

20

25

30

35

40

45

50

55





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 00 10 8565

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 812 011 A (WAKO PURE CHEM IND LTD) 10 December 1997 (1997-12-10) * page 2, line 5 - line 51 * * page 3, line 10 - line 13 * * page 3, line 24 - line 50 * * page 4, line 3 - line 29 *	1,2,5,7, 9-11	H01L21/306 H05K3/26 C11D7/26 B08B3/08 C11D1/02 C11D1/66
A	---	3,4,6,8	
X	FR 2 722 511 A (ONTRAK SYSTEMS INC) 19 January 1996 (1996-01-19) * page 1, line 1 - line 33 * * page 3, line 14 - page 4, line 4 * * page 6, line 15 - page 7, line 10 * * page 8, line 6 - page 10, line 18 * * page 16, line 9 - page 17, line 14; claims 8,13-22 *	1-3,5, 9-11	
X	WO 99 15609 A (OLIN MICROELECTRONIC CHEMICALS) 1 April 1999 (1999-04-01) * page 1, line 5 - line 15 * * page 6, line 1 - page 7, line 6 * * page 8, line 1 - line 17 * * page 10, line 10 - line 21 * * page 11, line 5 - line 20 * * page 12, line 5 - page 13, line 4 * * page 14, line 4 - line 11 *	1-3,5,6, 8-10	TECHNICAL FIELDS SEARCHED (Int.Cl.7)  H01L C11D H05K B08B
X	WO 98 36045 A (SMALL ROBERT J ;EKC TECHNOLOGY INC (US)) 20 August 1998 (1998-08-20) * page 1, paragraph 16 - line 23 * * page 3, line 1 - line 29 * * page 6, line 15 - page 7, line 3 * * page 10, line 8 - page 12, line 3 * * page 13, line 24 - page 14, line 5 *	1-3,5,7, 9-11	
	---		
	-/--		
The present search report has been drawn up for all claims			
Place of search <b>BERLIN</b>		Date of completion of the search <b>10 August 2000</b>	Examiner <b>Klopfenstein, P</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons</p> <p>&amp; : member of the same patent family, corresponding document</p>			

EPO FORM 150 03 82 (P04011)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 10 8565

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Incl.7)
X	US 5 695 572 A (THALHAMMER GERTRAUD ET AL) 9 December 1997 (1997-12-09) * column 1, line 6 - line 12 * * column 1, line 53 - column 2, line 14 * * column 2, line 30 - column 3, line 2 *	1-3,5-7,9	
A	---	10,11	
X	EP 0 678 571 A (BAKER J T INC) 25 October 1995 (1995-10-25) * page 2, line 1 - line 13 * * page 2, line 49 - page 3, line 9 * * page 3, line 30 - line 54 *	1-3,5-7,9,10	
A	---	11	
X	DE 42 09 865 A (WACKER CHEMITRONIC) 30 September 1993 (1993-09-30) * page 2, line 3 - line 31 * * page 2, line 46 - line 59 * * page 3, line 5 - line 22; claims 1,3,5 *	1-3,5,9,10	TECHNICAL FIELDS SEARCHED (Incl.7)
A	---	6,11	
A	PATENT ABSTRACTS OF JAPAN vol. 014, no. 411 (E-0973), 5 September 1990 (1990-09-05) -& JP 02 156530 A (TOSHIBA CORP;OTHERS: 01), 15 June 1990 (1990-06-15) * abstract * -----	1,4,6,9-11	
The present search report has been drawn up for all claims			
Place of search <b>BERLIN</b>		Date of completion of the search <b>10 August 2000</b>	Examiner <b>Klopfenstein, P</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &amp;: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04/2011)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 8565

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-08-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0812011 A	10-12-1997	JP 10072594 A	17-03-1998
FR 2722511 A	19-01-1996	DE 19525521 A	21-03-1996
		JP 8187475 A	23-07-1996
WO 9915609 A	01-04-1999	US 5977041 A	02-11-1999
		AU 9497398 A	12-04-1999
		EP 1017770 A	12-07-2000
WO 9836045 A	20-08-1998	US 5981454 A	09-11-1999
		EP 0909311 A	21-04-1999
US 5695572 A	09-12-1997	DE 4430217 A	29-02-1996
		DE 19515024 A	31-10-1996
		CN 1124763 A	19-06-1996
		DE 59506147 D	15-07-1999
		EP 0698917 A	28-02-1996
		FI 953947 A	26-02-1996
		JP 2709452 B	04-02-1998
		JP 8100195 A	16-04-1996
		KR 157702 B	01-12-1998
EP 0678571 A	25-10-1995	US 5466389 A	14-11-1995
		CA 2146036 A	21-10-1995
		JP 2670987 B	29-10-1997
		JP 7297158 A	10-11-1995
		KR 160372 B	16-11-1998
		SG 32336 A	13-08-1996
DE 4209865 A	30-09-1993	NONE	
JP 02156530 A	15-06-1990	NONE	

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

